

6 □□□□ □□□□□□ □□□ □□□□□□□□ □□□□□ □□□ □□□□□□□□

--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--

0000 00 000000000 000000 000000 CVD 000000 (0000000000 000000 000000) 00 000000 00 00000000 00 00 000000
 000000000 0000000000 0000 00 000000 00 00 0000000000 000000 0000 000000 00 0000000000 0000000000 00
 000000 00000 00 00 00000 00000000 00 000000000 0000000000 000000000 000000 0000 0000000 000000 00 00 0000
 0000, "000000 0000" 0000000000 000000 00 0000 0000000000 00000000 00 0000 00000 0000 00 00 00000 0000 00 00 00000 00
 00000000000000000000 00 00000 00 000000 00 00000 00 0000000000 0000 00 00000 00 00 00000 00 00 00000 00 00000 0000
 0000000000 00 000000000 00000 00 00000 00000000 000000 00 00000 000000000 0000 00 00000000 00 00 000000 00 00 00000
 00 000000000000 00000 00 000000000000 00000000 00 00000 000000000 0000 00 00000000 00 00 00000000 00 00 00000
 00 0000000000000 00000 00 000000000000 000000 00 000000 00 00000000 00 000000 00 0000000000

6 □□□□ □□□□□□ □□□ □□□□□□□□ □□□□□ □□□□□□□□

- [illegible]

[illegible]

2140x3300mm, 2250x3300mm, 2140x1650mm, 2440x1650mm, 2440x3300mm, □□, □□□□□□□ □□□□
□□□□□□ □□ □□□□□□□ □□ □□□□□ □□□□ □□ □□□□ □□□

- windows 窗, 窗戶, 窗框, 窗台, 窗簾, 窗戶, 窗戶
- 窗戶, 窗戶, balustrades, 窗戶, 窗戶

Online Coated Reflective Glass Performance Data

Color	Thickness	Visible Light Transmittance	Visible Light Reflectance	UV Light Transmittance	Direct Light Transmittance	Direct Sunlight Reflectance	Total Solar Transmittance	shading coefficient (SC)	RHG	K Value (Summer Daytime)	K Value (Winter Night)
Euro Bronze	5mm	25.78%	16.60%	2.73%	35.79%	14.70%	47.73%	0.54	0.505	5.272	5.843
	6mm	20.45%	16.32%	2.03%	29.70%	14.85%	43.08%	0.48	0.463	5.243	5.808
Euro Grey	5mm	24.96%	15.62%	3.85%	32.96%	14.02%	45.76%	0.51	0.488	5.272	5.843
	6mm	21.26%	15.36%	3.05%	28.01%	13.37%	42.15%	0.47	0.457	5.243	5.808
Dark Grey	5mm	24.93%	17.13%	4.68%	32.67%	15.22%	45.24%	0.51	0.482	5.272	5.843
	6mm	20.62%	14.09%	3.50%	27.39%	12.71%	41.83%	0.47	0.455	5.243	5.808
Light Blue	5mm	28.47%	31.69%	4.39%	30.29%	22.01%	41.80%	0.47	0.445	5.256	5.824
	6mm	25.33%	31.63%	3.54%	28.14%	21.17%	38.85%	0.44	0.419	5.243	5.808
Dark Blue	5mm	23.35%	13.46%	12.07%	43.49%	18.44%	52.66%	0.59	0.548	5.272	5.843
	6mm	18.79%	11.79%	10.23%	38.68%	17.19%	49.32%	0.55	0.517	5.243	5.808
F-Green	5mm	28.40%	35.11%	3.13%	24.11%	19.91%	37.61%	0.42	0.409	5.272	5.843
	6mm	26.43%	34.12%	2.76%	20.76%	18.66%	35.37%	0.40	0.39	5.243	5.808
Dark Green	5mm	27.31%	26.52%	4.36%	28.14%	16.63%	41.46%	0.47	0.446	5.272	5.843
	6mm	25.40%	24.35%	4.06%	26.15%	15.15%	40.30%	0.45	0.438	5.243	5.808
Silver White	5mm	50.58%	34.10%	13.87%	58.00%	25.85%	61.89%	0.70	0.625	5.272	5.843
	6mm	42.75%	36.11%	9.47%	52.31%	28.29%	56.99%	0.64	0.578	5.243	5.808

For reference only

□□□□□ □□□□□ □□□□□□□□ □□□□□ □□□□□□□ □□□□



00000 00000 000000000 00000 000000



00000 00000 000000000 00000 0000000 000 00 000 00

