

6 mm

6 mm

CVD (CVD)

6 mm

- (e < 0.1)
- UV
- UV
- UV
- UV
- UV
- UV
- UV

6 mm

2140x3300mm2250x3300mm 2140x1650mm2440x1650mm2440x3300mm

Windows

- Windows
- Windows

Online Coated Reflective Glass Performance Data

Color	Thickness	Visible Light Transmittance	Visible Light Reflectance	UV Light Transmittance	Direct Light Transmittance	Direct Sunlight Reflectance	Total Solar Transmittance	shading coefficient (SC)	RHG	K Value (Summer Daytime)	K Value (Winter Night)
Euro Bronze	5mm	25.78%	16.60%	2.73%	35.79%	14.70%	47.73%	0.54	0.505	5.272	5.843
	6mm	20.45%	16.32%	2.03%	29.70%	14.85%	43.08%	0.48	0.463	5.243	5.808
Euro Grey	5mm	24.96%	15.62%	3.85%	32.96%	14.02%	45.76%	0.51	0.488	5.272	5.843
	6mm	21.26%	15.36%	3.05%	28.01%	13.37%	42.15%	0.47	0.457	5.243	5.808
Dark Grey	5mm	24.93%	17.13%	4.68%	32.67%	15.22%	45.24%	0.51	0.482	5.272	5.843
	6mm	20.82%	14.09%	3.50%	27.39%	12.71%	41.83%	0.47	0.455	5.243	5.808
Light Blue	5mm	28.47%	31.89%	4.39%	30.29%	22.01%	41.80%	0.47	0.445	5.256	5.824
	6mm	25.33%	31.63%	3.54%	28.14%	21.17%	38.85%	0.44	0.419	5.243	5.808
Dark Blue	5mm	23.35%	13.46%	12.07%	43.49%	18.44%	52.66%	0.59	0.548	5.272	5.843
	6mm	18.79%	11.79%	10.23%	38.68%	17.19%	49.32%	0.55	0.517	5.243	5.808
F-Green	5mm	28.40%	35.11%	3.13%	24.11%	19.91%	37.61%	0.42	0.409	5.272	5.843
	6mm	26.43%	34.12%	2.76%	20.76%	18.66%	35.37%	0.40	0.39	5.243	5.808
Dark Green	5mm	27.31%	26.52%	4.36%	28.14%	16.63%	41.46%	0.47	0.446	5.272	5.843
	6mm	25.40%	24.35%	4.06%	26.15%	15.15%	40.30%	0.45	0.438	5.243	5.808
Silver White	5mm	50.58%	34.10%	13.87%	58.00%	25.85%	61.89%	0.70	0.625	5.272	5.843
	6mm	42.75%	38.11%	9.47%	52.31%	28.29%	56.99%	0.64	0.578	5.243	5.808

For reference only

6 mm □□□□□□□□ □□



6 mm □□□□□□□□



6 mm □□□□□□□□□□

